

IN THE CLAIMS:

1.-14. (Cancelled)

15. (New) A molding composition consisting essentially of:

- (A) 40 to 90 parts by weight of polyamide;
- (B) 0.5 to 50 parts by weight of ethylene-propylene rubbers or ethylene-propylenediene rubbers;
- (C) 0 to 50 parts by weight of at least one member selected from the group consisting of glass fibers, glass spheres and silicates;
- (D) 0.1 to 15 parts by weight of a member selected from the group consisting of phenol-formaldehyde resin, an oligomeric compound having at least 2 phenolic hydroxyl groups per molecule and a polymeric compound having at least 2 phenolic hydroxyl groups per molecule, said oligomeric compound and polymeric compound being different from said phenol-formaldehyde resins;
- (E) 0 to 50 parts by weight of a copolymer of styrene, acrylonitrile and maleic acid anhydride; and
- (F) 0 to 30 parts by weight of a vinyl(co)polymer,

wherein the sum of the parts by weight of all the components is 100.

16. (New) The composition according to Claim 15, wherein the polyamide is at least one member selected from the group consisting of (co)polyamide-6, (co)polyamide-66, polyamides whereof the acid component included at least one acid selected from the group consisting of terephthalic acid, isophthalic acid, suberic acid, sebacic acid, azelaic acid, adipic acid and cyclohexanedicarboxylic acid and wherein the diamine component includes at least one member selected from the group consisting of m-methyl-diaminodicyclohexyl methane and the isomer mixture of 2,2,4- and/or 2,4,4-trimethylhexamethylene diamine.

17. (New) The composition according to Claim 15, wherein the polyamide is at least one member selected from the group consisting of (co)polyamide-6 and (co)polyamide-66.

18. (New) The composition according to Claim 15, wherein component (F) is a (co)polymer of

F.1 from 50 to 99 wt.% of at least one member selected from the group consisting of vinyl aromatics, vinyl aromatics substituted in the ring and (meth)acrylic acid-(C₁-C₈)-alkyl ester, and

F.2 from 1 to 50 wt.% of at least one member selected from the group consisting of vinyl cyanides and (meth)acrylic acid-(C₁-C₈)-alkyl esters,

the wt.% being relative to the weight of component (F).

19. (New) A molded article comprising the composition of Claim 15.